

# TAPECONCURRENT

## Product datasheet 4414

ITEMS	UNIT	SPEC. VALUE	TESTMETHOD
<b>Dimension &amp; Tolerances</b>			
Inside diameter of roll:	mm	32 +/- 1.0	ASTM D-1000
Thickness:	mm	0.152 ±10%	ASTM D-1000
<b>Composition</b>			
Backing:		Plasticized PVC	
Thickness:	mm	0.130	
Glue:		Rubber base	
<b>Physical &amp; Chemical Prop</b>			
180° Peel adhesion			
To steel:	kgf/25mm	0.35↑	ASTM D-1000
To backing:	kgf/25mm	0.35↑	ASTM D-1000
Unwind force:	gf/19mm	350↑	ASTM D-1000
Tensile strenght:	kgf/25mm	6.0↑	ASTM D-1000
Elongation:	%	100↑	ASTM D-1000
Dielectric Breakdown:	kv	6↑	ASTM D-1000
<b>Storage</b>			
Condition:		73°F, 65% R.H.	
Validity:	Year	1	

Customer sneed to test and confirm products for the actual operational requirement and purpose or inform us to supply the futher introduction and service.  
Above information is for reference only and should not be as inpection standard.