

TAPECONCURRENT**TAPE OP MAAT**

Technical datasheet

2772

Gummed reinforced paper tape

Material

Support kraft paper
Adhesive Plant based
Fibre core Fibreglass

Technical data

Technical Property	Value	Unit
Top material grammage	40	g/m ² (+/- 4%)
Bottom material grammage	40	g/m ² (+/- 4%)
Core	50	mm
Length	150	m (+/- 2%)
Width	70	mm (+/- 1%)
Lamination melting temperature (DIN 52011)	+ 70	°C
Longitudinal breaking strength (DIN EN ISO 1924-2)	11	kN/m
Transverse breaking strength (DIN EN ISO 1924-2)	6,0	kN/m

DISCLAIMER

All statements, technical information and recommendations herein are based on tests we believe to be reliable, but the accuracy and completeness thereof is not guaranteed, and the following is made in lieu of all warranties, expressed or implied, including the implied warranties of merchantability and fitness for purpose: Seller's and Manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Before using, User shall determine the suitability of the product for its intended use, and User assumes all risk and liability whatsoever in connection therewith. Seller reserves the right to improve the product and accordingly change the specification without notice. Neither Seller nor Manufacturer shall be liable either in tort or in contract for any loss or damage, direct, incidental, or consequential, arising out of the use of or the inability to use the product. No statement or recommendation not contained herein shall have any force or effect unless in an agreement signed by officers of or Seller and Manufacturer.