

TAPECONCURRENT**TAPE OP MAAT**

Technical datasheet

6835AC

Double-sided PE Foamtape

Material

Support PE
Adhesive Solution Acrylic

Technical data

| Technical Property | Value | Unit |
|-------------------------------------|-------------------------------------|------------------|
| Foam density | 33 | Kg per cu. metre |
| Release liner thickness | 0.075 | |
| 180-degree peel adhesion | Greater than internal foam strength | |
| Liner release | 10 | N/m |
| Foam hardness | 44 | Shore scale |
| Force to compress 25% | 40 | kPa |
| Tensile strength M.D. | 400 | kPa |
| Tensile strength C.D. | 265 | Kpa |
| Elongation at break M.D. | 130 | % |
| Elongation at break C.D. | 125 | % |
| Service temperature | -20 to +90 | °C |
| Recommended application temperature | +5 to +25 | °C |
| Resistance to UV, Weathering | Excellent | |
| Resistance to Oxidation, fungi | Excellent | |
| Shelf life | 12 | Months |

Test Methods: BS 7116

DISCLAIMER

The information supplied is accurate to our best knowledge and is based upon all current data available to it. The information is given in good faith and for guidance only. All data is based upon average values. Properties quoted are typical and do not therefore constitute a specification. Customers must complete their own assessment of the product for its intended application under their own conditions. Our technical advice is to be regarded as an expression of opinion only and although such an advice is given in good faith, it shall not, in any circumstances, be regarded as the basis of or as being a representation or statement of fact. This applies also where propriety or protective rights of third parties are involved. Any liability arising in respect of our products will be strictly limited to the value of those products charged to the customer and shall not extend to any consequential loss whatsoever and howsoever arising. Freedom from Patent Rights must not be assumed. This document does not form part of any contract with a customer.