



# Technical datasheet

## 8390

### Double-sided tissue tape

#### Technical data

| Technical Property                  | Value            | Unit   |
|-------------------------------------|------------------|--------|
| Thickness, adhesive + carrier       | 0.080            | Mm     |
| Release liner thickness             | 0.065            |        |
| 180-degree peel adhesion            |                  |        |
| Open side                           | 900              | N/m    |
| Closed side                         | 900              | N/m    |
| Polyester loop tack                 |                  |        |
| Open side                           | 850              | N/m    |
| Closed side                         | 850              | N/m    |
| Liner release                       | 10               | N/m    |
| Tensile strength                    | 1200             | N/m    |
| Elongation at break                 | 10               | %      |
| Service temperature                 | -10 to +60       | °C     |
| Recommended application temperature | +5 to +25        | °C     |
| Shear adhesion, 1kg at 23°C         | Greater than 100 | Hours  |
| Shelf life                          | 12               | Months |

#### Test Methods

BS3924:1978

The individual ingredients of the adhesive have been tested and approved for indirect food contact to the FDA specification 175.105

#### DISCLAIMER

The information supplied is accurate to our best knowledge and is based upon all current data available to it. Properties quoted are typical and do not therefore constitute a specification. Customers must complete their own assessment of the product for its intended application under their own conditions. Our technical advice is to be regarded as an expression of opinion only and although such an advice is given in good faith, it shall not, in any circumstances, be regarded as the basis of or as being a representation or statement of fact. This applies also where propriety or protective rights of third parties are involved. Any liability arising in respect of our products will be strictly limited to the value of those products charged to the customer and shall not extend to any consequential loss whatsoever and howsoever arising. Freedom from Patent Rights must not be assumed. This document does not form part of any contract with a customer.