

TAPECONCURRENT

TAPE OP MAAT

25/03/2022

Technische datasheet 5850 -5859

Unit: cd/1xm²

Observation Angle	Entrance Angle	Measured Value			Standard Value
		Y4	Y5	Y6	White color
12'	5°	43	40	39	35
	30°	23	26	26	18
	40°	12	16	15	7.0
20'	5°	33	31	29	25
	30°	19	20	18	12
	40°	11	11	13	6.0
2°	5°	9	10	7	4.0
	30°	6	7	9	1.8
	40°	5	6	5	1.0

Material/Colour	Av. LRV	Range
Red	14	2
Orange	41	3
Yellow	65.25	2
Green	41	4
Blue	7	2
White	85	0
Brown	15.7	0.88
Black	0	0
Black/Yellow (Black)	0	0
Black/Yellow (Yellow)	62	2
Red/White (Red)	13.5	1
Red/White (White)	84	0

*The test procedure follows Lucideon In House Test Method WW22, and complies with the requirements of
BS.8493:2008+A1:2010.*

All the above data is for reference only.