

TAPECONCURRENT

TAPE OP MAAT

Technische datasheet 6194

PVC Single Sided Foam Tape - Hard,
Black, Waterseal

DESCRIPTION

6194 is primarily a foam compression sealant. The product is black. The foam is predominantly closed celled and is a hard foam. An acrylic pressure sensitive adhesive is coated on one side, and the product has a paper release liner on the other non-adhesive face. 6194 will act as a water-seal and air/dust seal when compressed.

APPLICATIONS

- Forms a compression water seal.
- For preventing electrolytic corrosion. For heavy duty cushioning.
- Forms a compression air / dust seal. For gap filling.
- For high load bearing applications.

PRODUCT BENEFITS

- Minimum 30% compression required to effect a water seal. Service temperature: -30°C to +70°C.
- Application temperature: +10°C to +40°C. Shelf life of 1 year from date of dispatch.
- Coated on one side with a high quality pressure sensitive acrylic adhesive. Good resistance to dilute acids and alkalis.
- Paper release liner on the non-adhesive face, reducing dimensional change during application. Very good ultraviolet {UV} light resistance.

- Resistance to abrasion,
- corrosion and moisture.
- Suitable for indoor and outdoor environments. No known hazards associated with this product.
- Pre-determined dimensional
- sealant reduces waste. Clean to use / clean edge finish.

Accreditation:

Fire rated to DIN 4102 part 1, B2.

AbP DIN EN 13501-1 : 2010 Class E Fire classification.

Conforms to European Directive 2000/53 EC (lead, chromium VI, mercury, cadmium free)

TECHNICAL PROPERTIES

Technical Property	Nominal Value	Unit	Test Method
10 Minute 180° Peel Adhesion	5	N/25mm	F9
Force To Compress By 30 %	6.1	N/cm ²	F4
Compression Deflection After 1 Minute	5.0	N/cm ²	F4
Foam Density	220	Kg/m ³	F2
Shore Hardness {OO} Scale	50	"OO"	F16
Elongation at Break	>180	%	F17
Tensile Strength	66	N/cm ²	F17
Thermal Conductivity (k)	0.043	Wm ⁻¹ K ⁻¹	Lee's Disc

RECOMMENDATIONS

The rolls should be stored flat on their cut edges in the original packaging. The product must be protected from dust, heat, moisture, direct sunlight and solvent fumes. Storage temperature between +10°C and

+30°C. Under these conditions, the shelf life of the tape is 12 months from the date

of dispatch. Surfaces should be clean, dry and free of dust, grease, oil or other

contaminants.

Customers are recommended to make their own assessment of our products under their own conditions, for their own requirements.