

# TAPECONCURRENT

## Technical datasheet

### 6607 Double sided PE foam mounting tape

**Liner:**

Siliconized white paper 90 g/sqm.

**Carrier:**

White closed-cell polyethylene high density foam

**Adhesive:**

Rubber based

**Applications:**

For applications where High Shear and High performance are needed and where a low density foam is required

**Adhesion with Substrates:**

<b>Metal / Aluminium</b>	High	<b>Textile/Cotton</b>	High
<b>Glass / Ceramics</b>	High	<b>Rubber/EPDM</b>	High
<b>Painted Surface</b>	High	<b>Acrylic/PET</b>	High
<b>Wood/Board/Paper</b>	High	<b>Polystyrene</b>	High
<b>Soft PVC</b>	Low	<b>PP/PE/PS</b>	High
<b>Rigid PVC</b>	High	<b>Smooth substrate</b>	High
<b>PC/ABS</b>	High	<b>Rough substrate</b>	High

Resistant to water, detergents and alcohol. Low resistance to plasticizers and low outdoor resistance. Not recommended for use in contact with aliphatic or aromatic hydrocarbons. 2 years when stored at 15 to 25°C and  $\pm 50$  % relative humidity.

**Technical description:**

Elongation at break  
Peel 180° >  
Shear(1kg 25mm x 25mm)  
Total thickness  
Minimum application temperature  
End-use temperature

**Technical values:**

300%  
16N/25mm  
> 5000 H  
1,1mm  
+10 °C  
-40 °C to +60 °C

*All statements, technical information and recommendations herein are based on tests we believe to be reliable, but the accuracy and completeness thereof is not guaranteed and the following is made in lieu of all warranties, expressed or implied, including the implied warranties of merchantability and fitness for purpose: Seller's and Manufacturer's only obligation shall be to replace such quantity of the product proved to be defective. Before using, User shall determine the suitability of the product for its intended use, and User assumes all risk and liability whatsoever in connection therewith. Seller reserves the right to improve the product and accordingly change the specification without notice. Neither Seller nor Manufacturer shall be liable either in tort or in contract for any loss or damage, direct, incidental or consequential, arising out of the use of or the inability to use the product. No statement or recommendation not contained herein shall have any force or effect unless in an agreement signed by officers of or Seller and Manufacturer.*