

# TAPECONCURRENT

## Product Data sheet Paper Masking Tape with foil 9901

### FILM

<b>Item</b>	Pre-Taped Masking Film(Indoor Painting Purpose)
<b>Usage</b>	Indoor painting works
<b>Material (film)</b>	100% Virgin of High Density Polyethylene
<b>Color</b>	Transparent(HDPE Natural Color)
<b>Thickness</b>	0.0009mm.+/- 3%
<b>Width</b>	300mm to 2700mm
<b>Heat resistance</b>	10 °C – max 110 °C
<b>Corona treatment</b>	44 Dyne by treator
<b>Specification</b>	<ul style="list-style-type: none"><li>1)Sticks immediately to the surface of the car when places on it.</li><li>2)Very flexible, suits the shape of the car and does not tear.</li><li>3)Transparent, can be cut in the exact size.</li><li>4)Easy to be torn by hand without dispenser</li><li>5)Closed surface structure. The paint can not get through.</li><li>6)Absolutely waterproof, even when used with waterborne paint.</li><li>7)Resistant to compressed air, can be blown dry.</li><li>8)Can be compressed to minimum dimensions. Less waste.</li></ul>

## Tape:

<b>Item</b>	Pre-Taped Masking Film(Indoor Painting Grade)
<b>Usage</b>	Construction or indoor painting purpose
<b>Material (tape)</b>	Crepe tape
<b>Color</b>	Light Beige Color
<b>Thickness</b>	145±10 $\mu$ m
<b>Adhesive</b>	≥6#
<b>180 ° tear off</b>	≥0.65kg/25mm
<b>Adhesive time keep</b>	≥3 hours
<b>Tensile strength</b>	≥25 N/cm
<b>Elongation strength</b>	≤20%
<b>Max. temperature resistant</b>	60°C / 30 min
<b>Valid time</b>	At least 6 months keeping products in 20~30°C & 50~70% humidity
<b>Specification</b>	1)Good adhesion 2)No remaining residue on the surface after works

### Disclaimer:

All statements, technical information and product recommendations are based on tests in our laboratories we believe to be reliable. In all cases the user should however determine the suitability of the product for his intended use and user assumes all risk and liability whatsoever in connection therewith. Neither seller or manufacturer shall be reliable for any loss or damage – direct, incidental or consequential – arising from the use of the product. Details of test methods are available on request.